

PROPERTY	TEST METHOD	FREQUENCY ⁽¹⁾	UNIT Imperial	1040038
SPECIFICATIONS				
Thickness (min. avg.)	ASTM D-5199	Every roll	mils	30.0
Thickness (min.)	ASTM D-5199	Every roll	mils	27.0
Resin Density	ASTM D-1505	1/Batch	g/cc	> 0.932
Melt Index - 190/2.16 (max.)	ASTM D-1238	1/Batch	g/10 min	1.0
Sheet Density (8)	ASTM D-792	Every 10 rolls	g/cc	≥ 0.940
Carbon Black Content (9)	ASTM D-4218	Every 2 rolls	%	2.0 - 3.0
Carbon Black Dispersion	ASTM D-5596	Every 10 rolls	Category	Cat. 1 & Cat. 2
OIT - standard (avg.)	ASTM D-3895	Per formulation	min	100
Tensile Properties (min. avg) (2)	ASTM D-6693	Every 2 rolls		
Strength at Yield			ppi	66
Elongation at Yield			%	13
Strength at Break			ppi	122
Elongation at Break			%	700
Tear Resistance (min. avg.)	ASTM D-1004	Every 5 rolls	lbf	21
Puncture Resistance (min. avg.)	ASTM D-4833	Every 5 rolls	lbf	60
Dimensional Stability	ASTM D-1204	Certified	%	± 2
Stress Crack Resistance (SP-NCTL)	ASTM D-5397	1/Batch	hr	500
Oven Aging - % retained after 90 days	ASTM D-5721	Per formulation		
HP OIT (min. avg.)	ASTM D-5885		%	80
UV Resistance - % retained after 1600 hr	GRI-GM-11	Per formulation		
HP-OIT (min. avg.)	ASTM D-5885		%	50
SUPPLY SPECIFICATIONS (Roll dimensions may vary ±1%)				
Roll Dimension - Width	-		ft	22.3
Roll Dimension - Length	-		ft	1,000
Area (Surface/Roll)	-		sf	22,300

NOTES

1. Testing frequency based on standard roll dimensions and one batch is approximately 180,000 lbs (or one railcar).
2. Machine Direction (MD) and Cross Machine Direction (XMD or TD) average values should be on the basis of 5 specimens each direction.
8. Correlation table is available for ASTM D792 vs ASTM D1505. Both methods give the same results.
9. Correlation table is available for ASTM D1603 vs ASTM D4218. Both methods give the same results.

* All values are nominal test results, except when specified as minimum or maximum.

* The information contained herein is provided for reference purposes only and is not intended as a warranty of guarantee. Final determination of suitability for use contemplated is the sole responsibility of the user. SOLMAX assumes no liability in connection with the use of this information.

Solmax is not a design professional and has not performed any design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation or specification.